

apilon 52® D1 40L

Thermoplastic Polyurethane Elastomer (Polyester)

API SpA

Message:

apilon 52®D1 40L is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) product. It can be processed by injection molding and is available in Europe. apilon 52®The application areas of D1 40L include engineering/industrial accessories, electrical/electronic applications, electrical appliances, tools and home applications.

- Features include:
- environmental protection/green
 - Good UV resistance
 - low temperature resistance
 - chemical resistance
 - Wear-resistant

General Information			
Features	Good UV resistance		
	Recyclable materials		
	Good wear resistance		
	Low temperature resistance		
	Hydrolysis resistance		
	Oil resistance		
Uses	Handle		
	Wheels		
	Conveyor belt repair		
	Electrical/Electronic Applications		
	Electrical appliances		
	Washer		
	Power/other tools		
	Pipe fittings		
	Household goods		
	Sporting goods		
	Coating application		
Forms	Particle		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A, 15 seconds	89		ASTM D2240
Shaw D, 3 seconds	42		ASTM D2240

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	45.0	MPa	ASTM D638
100% strain	6.50	MPa	ASTM D638
300% strain	13.0	MPa	ASTM D638
Tensile Elongation (Break)	530	%	ASTM D638
Flexural Modulus	35.0	MPa	ASTM D790
Abrasion Resistance	30.0	mm ³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	105	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (-20°C)	No Break		ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 110	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.070	%	
Rear Temperature	180 - 190	°C	
Middle Temperature	185 - 200	°C	
Front Temperature	190 - 215	°C	
Nozzle Temperature	200 - 230	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection Pressure	50.0 - 100	MPa	
Injection Rate	Slow-Moderate		
Injection instructions			
Back Pressure: Medium to LowLocking Pressure: High			
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 - 110	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.070	%	
Cylinder Zone 1 Temp.	160 - 185	°C	
Cylinder Zone 2 Temp.	170 - 200	°C	
Cylinder Zone 3 Temp.	175 - 210	°C	
Cylinder Zone 4 Temp.	180 - 220	°C	
Die Temperature	170 - 210	°C	
Extrusion instructions			
L/D Ratio: 20:1 to 30:1Compression Ratio: 1:2.5 to 1:3			
NOTE			
1.	Without Notch		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

