

ELASTOSIL® E 303

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1

Coatings, Paints & Coatings

General Information			
Uses	Adhesives		
	Bonding		
	Sealants		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Colorless		
Flash Point	28.0	°C	DIN 51376
Viscosity	0.50	Pa·s	DIN EN ISO 2555
Skin Forming Time ¹ (23°C)	5.0	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	30		ISO 868
Tensile Strength	5.00	MPa	ISO 37
Tensile Elongation at Break	400	%	ISO 37
Ignition Temperature	345	°C	DIN 51794
NOTE			

1. 50% R.H

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT