

# LNP™ LUBRILOY™ D20001 compound

Polycarbonate

SABIC Innovative Plastics

## Message:

LNP LUBRILOY\* D20001 is a compound based on Polycarbonate resin containing Flame Retardant, Proprietary Lubricant. Added features of this material include: Flame Retardant.

Also known as: LNP\* LUBRILOY\* Compound D-FR ECO

Product reorder name: D20001

General Information			
UL YellowCard	E207780-101345223		
Additive	Lubricant		
Features	Lubrication		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.50	%	ASTM D955
Transverse flow: 24 hours	0.60	%	ASTM D955
Vertical flow direction: 24 hours	0.57	%	ISO 294-4
Flow direction: 24 hours	0.53	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.12	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- <sup>1</sup>	2550	MPa	ASTM D638
--	2600	MPa	ISO 527-2/1
Tensile Strength			
Yield	67.3	MPa	ASTM D638
Yield	62.3	MPa	ISO 527-2
Fracture	60.2	MPa	ASTM D638
Fracture	54.5	MPa	ISO 527-2
Tensile Elongation			
Yield	4.5	%	ASTM D638
Yield	4.3	%	ISO 527-2
Fracture	6.5	%	ASTM D638
Fracture	6.7	%	ISO 527-2
Flexural Modulus			
--	2830	MPa	ASTM D790

--	2800	MPa	ISO 178
Flexural Strength			
--	103	MPa	ASTM D790
--	102	MPa	ISO 178
Coefficient of Friction			
With self-dynamics	0.091		ASTM D3702 Modified
With Self-Static	0.23		ASTM D3702 Modified
Wear Factor - Washer	30.0	10 <sup>-10</sup> in <sup>5</sup> -min/ft-lb-hr	ASTM D3702 Modified
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact			
23°C	140	J/m	ASTM D256
23°C <sup>2</sup>	6.9	kJ/m <sup>2</sup>	ISO 180/1A
Unnotched Izod Impact			
23°C	1600	J/m	ASTM D4812
23°C <sup>3</sup>	100	kJ/m <sup>2</sup>	ISO 180/1U
Instrumented Dart Impact (23°C, Energy at Peak Load)	51.0	J	ASTM D3763
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	97.2	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	89.4	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span <sup>4</sup>	94.0	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	6.6E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	6.7E-5	cm/cm/°C	ASTM E831, ISO 11359-2
<b>Flammability</b>	<b>Nominal Value</b>		<b>Test Method</b>
Flame Rating (1.50 mm, Testing by SABIC)	V-0		UL 94
<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>	
Drying Temperature	82.2	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	249 - 260	°C	
Middle Temperature	254 - 266	°C	
Front Temperature	260 - 271	°C	
Processing (Melt) Temp	254 - 288	°C	
Mold Temperature	37.8 - 65.6	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
<b>NOTE</b>			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

