

Badamid® A70 S

Polyamide 66

Bada AG

Message:

Easy-flowing, nucleated injection moulding grade for low cycle times; For thin-walled components

General Information				
UL YellowCard		E189230-100625542		
Additive		Nucleating Agent		
Features		Good Flow		
		Nucleated		
Uses		Thin-walled Parts		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	8.5	--	%	
Equilibrium, 23°C, 50% RH	2.8	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus ¹ (23°C)	3100	1550	MPa	ISO 527-2/1
Tensile Stress ² (Yield, 23°C)	80.0	55.0	MPa	ISO 527-2/50
Tensile Strain ³ (Yield, 23°C)	4.5	21	%	ISO 527-2/50
Nominal Tensile Strain at Break ⁴ (23°C)	15	> 50	%	ISO 527-2/50
Flexural Stress ⁵ (23°C)	135	65.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength ⁶				ISO 179/1eA
-30°C	4.0	--	kJ/m ²	
23°C	6.0	14	kJ/m ²	
Charpy Unnotched Impact Strength ⁷				ISO 179/1eU
-30°C	No Break	--		
23°C	No Break	No Break		
Notched Izod Impact Strength ⁸				ISO 180/1A
-30°C	3.0	--	kJ/m ²	
23°C	5.0	11	kJ/m ²	

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature ⁹				
0.45 MPa, Unannealed	190	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	--	°C	ISO 75-2/A
Melting Temperature (DSC) ¹⁰	262	--	°C	ISO 3146
CLTE ¹¹				DIN 53752
Flow : 4.00 mm	8.5E-5	--	cm/cm/°C	
Transverse : 4.00 mm	8.5E-5	--	cm/cm/°C	
Maximum Service Temperature				IEC 216
20000 hrs	90	--	°C	
some hours	200	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity ¹²	1.0E+13	1.0E+10	ohms	IEC 60093
Volume Resistivity ¹³	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength				IEC 60243-1
-- ¹⁴	32	--	kV/mm	
in Air	--	600	kV/mm	
Relative Permittivity ¹⁵ (1 MHz)	3.60	5.00		IEC 60250
Dissipation Factor ¹⁶ (1 MHz)	0.025	0.20		IEC 60250
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm ¹⁷	V-2	--		
1.60 mm ¹⁸	V-2	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	2.0 to 4.0		hr	
Processing (Melt) Temp	280 to 300		°C	
Mold Temperature	60.0 to 80.0		°C	
NOTE				
1.	Test Specimen accordng to ISO 3167, Type A			
2.	Test Specimen accordng to ISO 3167, Type A			
3.	Test Specimen accordng to ISO 3167, Type A			
4.	Test Specimen accordng to ISO 3167, Type A			
5.	80x10x4 mm			

6.	80x10x4 mm
7.	80x10x4 mm
8.	80x10x4 mm
9.	110x10x4mm
10.	10 K/min, Compound for moulding
11.	> = 10x10x4 mm
12.	80x80x1 mm
13.	80x80x1 mm
14.	80x80x1 mm
15.	80x80x1 mm
16.	80x80x1 mm
17.	125x13x0.8 mm
18.	125x13x1.6 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

