

DENYL HT 4010

Polyphthalamide

Vamp Tech

Message:

PPA 40% glass fiber reinforced, excellent mechanicals properties, low water absorption, high chemical resistance and excellent operating temperature.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Good Chemical Resistance		
	Low to No Water Absorption		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.20	%	
Across Flow	0.60	%	
Water Absorption (Saturation)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	14500	MPa	ASTM D638
Tensile Strength (Yield)	220	MPa	ASTM D638
Tensile Elongation (Break)	2.2	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	9.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	60	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	280	°C	ASTM D648A
RTI Elec	150	°C	UL 746
RTI Imp	150	°C	UL 746
RTI Str	150	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	ASTM D257
Comparative Tracking Index (CTI)	600	V	UL 746
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	315	°C	
Mold Temperature	130	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHEG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT