# Hifax TRC 221X 1 BLACK

# Polypropylene Copolymer LyondellBasell Industries

### Message:

Hifax TRC 221X/1 BLACK is a 22% talc filled PP copolymer, with medium melt flow, good impact/stiffness balance, very low CLTE and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in BLACK color version.

For regulatory compliance information, see Hifax TRC 221X/1 BLACK Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 22% filler by weight		
Features	Low CLTE		
	Rigid, good		
	Copolymer		
	Impact resistance, good		
	Good UV resistance		
	Medium liquidity		
Uses	Car anti-collision bar		
	Application in Automobile Field		
	DI I		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	16.0	MPa	ISO 527-2
Flexural Modulus <sup>1</sup> (23°C)	1500	MPa	ISO 178/A
Flexural Stress <sup>2</sup> (23°C)	22.0	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	8.0	kJ/m²	ISO 180/1A
23°C	55	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa,	55.0	0.5	100 75 2 11
Unannealed)	55.0	°C	ISO 75-2/A
Vicat Softening Temperature	45.0	°C	ISO 306/B
NOTE			
1.	1.0 mm/min		

2. 1.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

