

Aaroprene® ATPO 3000 70A

Thermoplastic Polyolefin Elastomer

Aaron Industries Corp.

Message:

Aaroprene® ATPO 3000 70A is a polyolefin thermoplastic elastomer (TPO (POE)) material. This product is available in North America and is processed by extrusion or injection molding.

General Information			
Appearance	Available colors		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	10	g/10 min	ASTM D1238

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	70		ASTM D2240

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.07	MPa	ASTM D412
Taber Abrasion Resistance (1000 Cycles, H-18 Wheel)	180	mg	ASTM D1044

Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	4.83	MPa	ASTM D412
Tensile Elongation (Break)	550	%	ASTM D412

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-45.0	°C	ASTM D746

Injection	Nominal Value	Unit
Rear Temperature	177 - 216	°C
Middle Temperature	177 - 216	°C
Front Temperature	177 - 216	°C
Nozzle Temperature	188 - 221	°C
Processing (Melt) Temp	182 - 221	°C
Mold Temperature	10.0 - 65.6	°C
Back Pressure	0.0689 - 1.03	MPa
Screw Speed	100 - 200	rpm
Screw L/D Ratio	20.0:1.0	

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	182 - 204	°C
Cylinder Zone 2 Temp.	182 - 204	°C
Cylinder Zone 3 Temp.	188 - 210	°C

Cylinder Zone 4 Temp.	188 - 210	°C
Melt Temperature	193 - 216	°C
Die Temperature	193 - 216	°C
Take-Off Roll	21.1 - 48.9	°C

Extrusion instructions

Screen Pack: 20 to 60 meshCompression Ratio: 3:1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT