

# Ravaflex NBR FILLED

Acrylonitrile Butadiene Rubber

Ravago Group

## Message:

Chalk filled reprocessed copolymer of acrylonitrile and butadiene with a very good processibility and heat resistance.

General Information			
Filler / Reinforcement	chalk filler		
Features	Copolymer		
	Antioxidation		
	Workability, good		
	Heat resistance, medium		
Appearance	Amber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20 - 1.40	g/cm <sup>3</sup>	ASTM D297
Mooney Viscosity (ML 1+4, 100°C)	60 - 110	MU	ASTM D1646
ACN Content <sup>1</sup>	Medium		
Antioxidant Additive	Nonstaining		
Moisture Content (105°C)		%	Internal method
Ash content-1 hr (550°C)	25 - 30	%	ASTM D297
Packaging	1000	g	
Additional Information	Nominal Value	Unit	
It has a good resistance to aliphatic hydrocarbon oils, fuels and greases. It shows a low gas permeability and a good hot air resistance.			
NOTE			
1.	Internal Method		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT