

TECHNYL® B 218 V20 BLACK 21N

Polyamide 66/6 Copolymer
Solvay Engineering Plastics

Message:

TECHNYL® B 218 V20 Black 21N is a polyamide 66/6, reinforced with 20% of glass fibre, heat stabilized, for injection moulding. This grade offers an excellent combination between impact resistance, rigidity, thermal resistance and surface appearance.

General Information				
UL YellowCard		E44716-235615		
Filler / Reinforcement		Glass fiber reinforced material, 20% filler by weight		
Additive		heat stabilizer		
Features		Heat Stabilized - Inorganic		
		Good liquidity		
		Good demoulding performance		
		Excellent appearance		
Uses		Handle		
		Accessories		
		Application in Automobile Field		
Agency Ratings		EC 1907/2006 (REACH)		
		UL QMF22		
RoHS Compliance		RoHS compliance		
Appearance		Black		
Forms		Particle		
Processing Method		Injection molding		
Resin ID (ISO 1043)		PA66/6-GF20		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.28	--	g/cm ³	ISO 1183/A
Water Absorption				ISO 62
23°C, 24 hr	1.2	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.7	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	7500	5000	MPa	ISO 527-2/1A
Tensile Stress (Break, 23°C)	140	85.0	MPa	ISO 527-2/1A
Tensile Strain (Break, 23°C)	3.0	9.0	%	ISO 527-2
Flexural Modulus (23°C)	6000	3500	MPa	ISO 178
Flexural Stress (23°C)	230	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength (23°C)	7.0	9.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	45	83	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	8.0	13	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	230	--	°C	ISO 75-2/Af
Melting Temperature	242	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	6.0E+15	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+14	ohms·cm	IEC 60093
Dielectric Strength (2.00 mm)	32	28	kV/mm	IEC 60243-1
Dissipation Factor	0.010	0.11		IEC 60250
Comparative Tracking Index (Solution A)	450	350	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Oxygen Index	23	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	255 - 265		°C	
Middle Temperature	260 - 270		°C	
Front Temperature	270 - 280		°C	
Mold Temperature	70 - 100		°C	
Injection instructions				

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

For reinforced polyamide, Solvay recommends the use of steel with a high content of Carbon and purified for polishing to avoid or limit the abrasion.

For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). For Mould Temperature, in the case of parts where the surface roughness is required we can recommend a temperature of 90°C to 120°C with an optimum at 105°C.

The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT