

SLOVALEN® PC 52 T 20

Polypropylene

Plastcom

Message:

Modified copolymer PP for injection moulding with the content of 20% microground, floated, chemically modified talc. General application - packing material, garden flower-pots, toys, furniture industry, clamps, dowels, hinge, holders, office chairs, covers of chassis, motors, fenders. Increased toughness. Delivered in natural mode and in the full RAL colour scale. Heat stabilization enables the application in environment where it is subject to heat impact like eg. motor area.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Additive	Heat Stabilizer		
Features	Copolymer		
	Good Toughness		
	Heat Stabilized		
Uses	Automotive Applications		
	Automotive Under the Hood		
	Furniture		
	Living Hinges		
	Packaging		
	Toys		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PP		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	1.9	%	
Flow	1.8	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2
Tensile Stress (Yield)	25.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	2.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	15	kJ/m ²	
23°C	60	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	120	°C	ISO 75-2/B
Vicat Softening Temperature	85.0	°C	ISO 306/B
Melting Temperature (DSC)	150	°C	ISO 3146
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 to 250	°C	
Mold Temperature	40.0 to 50.0	°C	
Injection Pressure	70.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

