

BIPEX B0620GN

Polybutylene Terephthalate

Ginar Technology Co., LTD.

Message:

BIPEX B0620GN is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.00 mm)	0.35	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	148	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Modulus	8620	MPa	ASTM D790A
Flexural Strength	241	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	217	°C	ASTM D648
Peak Melting Temperature	220	°C	ASTM D789
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.0313 mm	HB		
0.0625 mm	HB		
0.125 mm	HB		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT