

TRIBOFORCE® PEEK C2300

Polyetheretherketone

LEIS Polytechnik - polymere Werkstoffe GmbH

Message:

polyetheretherketone, carbon fibre reinforced, wear and friction modified

General Information			
Filler / Reinforcement	Carbon Fiber		
Features	Lubricated		
Physical	Nominal Value	Unit	Test Method
Density	1.59	g/cm ³	ISO 1183
Molding Shrinkage ¹	0.050 to 0.20	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13000	MPa	ISO 527-2
Tensile Stress	145	MPa	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Coefficient of Friction ² (vs. Steel - Dynamic)	0.19		ASTM G137
Wear Factor ³ (5.0 MPa, 1.0 m/sec)	100	10 ⁻⁸ mm ³ /N·m	ASTM G137
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	35	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	340	°C	ISO 11357-3
Additional Information	Nominal Value		
Temperature of Use - Long-Time			
< 130°C	Yes		
130 to 200°C	Yes		
200 to 260°C	Yes		
260 to 300°C	Yes		
NOTE			
1.	60mm x 60mm x 2mm		
2.	5 MPa, 1 m/s, dry		
3.	Steel		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

