

LNP™ COLORCOMP™ JX91550 compound

Polyethersulfone
SABIC Innovative Plastics

Message:

LNP COLORCOMP* JX91550 is a compound based on Polyethersulfone resin containing Unfilled Custom Color.
Also known as: LNP* COLORCOMP* Compound PDX-J-91550
Product reorder name: JX91550

General Information			
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.49	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.60 - 0.80	%	ASTM D955
Transverse flow: 24 hours	0.70 - 0.90	%	ASTM D955
Vertical flow direction: 24 hours	0.70 - 0.90	%	ISO 294-4
Flow direction: 24 hours	0.60 - 0.80	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.77	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2940	MPa	ASTM D638
--	2830	MPa	ISO 527-2/1
Tensile Strength			
Yield	77.4	MPa	ASTM D638
Yield	78.0	MPa	ISO 527-2
Fracture	58.4	MPa	ASTM D638
Fracture	53.0	MPa	ISO 527-2
Tensile Elongation			
Yield	5.6	%	ASTM D638
Yield	6.2	%	ISO 527-2
Fracture	14	%	ASTM D638
Fracture	23	%	ISO 527-2
Flexural Modulus			
--	2900	MPa	ASTM D790
--	2930	MPa	ISO 178
Flexural Strength			
--	123	MPa	ASTM D790
--	118	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			

23°C	53	J/m	ASTM D256
23°C ²	4.3	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	No Break		ASTM D4812, ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	19.2	J	ASTM D3763
--	32.4	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	177	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ³	188	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	5.1E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	5.1E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	5.2E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121 - 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	343 - 354	°C	
Middle Temperature	360 - 371	°C	
Front Temperature	371 - 382	°C	
Processing (Melt) Temp	354 - 371	°C	
Mold Temperature	138 - 149	°C	
Back Pressure	0.344 - 0.689	MPa	
Screw Speed	60 - 100	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT