

# LARIPUR® LPR 70D60

Thermoplastic Polyurethane Elastomer (Polyether)

COIM S.p.A.

## Message:

LARIPUR® LPR 70D60 is a thermoplastic polyurethane elastomer (polyether)(TPU-polyether) material. This product is available in North America, Latin America or Europe. The processing method is injection molding.

LARIPUR® The main features of LPR 70D60 are:

Good flexibility

good weather resistance

chemical resistance

Wear-resistant

LARIPUR® Typical application areas of LPR 70D60 are: water pipes/pipes/drinking water

General Information			
Features	Flexibility at low temperatures		
	Good wear resistance		
	Good chemical resistance		
	Good weather resistance		
Agency Ratings	NSF 61		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	72		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	950	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain	30.3	MPa	ASTM D412
100% strain	33.2	MPa	ASTM D412
300% strain	55.1	MPa	ASTM D412
Tensile Strength (Break)	70.0	MPa	ASTM D412
Tensile Elongation (Break)	310	%	ASTM D412
Tear Strength	230	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	152	°C	ASTM D1525
Additional Information			

Abrasion loss, DIN 53516: 40 mm<sup>3</sup>Tosion Test, ASTM D 1043, 20° C: 232 MPaTosion Test, ASTM D 1043, -20° C: 472 MPaImpact Test, ASTM D 256, -20° C: 7.5 KJ/m<sup>2</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

