

Anjacom® 450-GF30

Polybutylene Terephthalate
Almaak International GmbH

Message:

Anjacom® 450-GF30 is a Polybutylene Terephthalate (PBT) material filled with 30% glass fiber. It is available in Europe for injection molding. Primary attribute of Anjacom® 450-GF30: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.55	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	20.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	0.20	%	
Water Absorption			ISO 62
23°C, 24 hr	0.40	%	
Equilibrium, 23°C, 50% RH	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2/1
Tensile Stress (Break)	140	MPa	ISO 527-2/5
Tensile Strain (Break)	2.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	60	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	°C	ISO 75-2/A
Vicat Softening Temperature	215	°C	ISO 306/B50
Melting Temperature (DSC)	224	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Electric Strength	30	kV/mm	IEC 60243-1
Comparative Tracking Index	350	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	4.0 to 10	hr	

Suggested Max Moisture	0.020	%
Processing (Melt) Temp	250 to 270	°C
Mold Temperature	80.0 to 110	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

