

PPR PA6602

Polyamide 66
Premier Plastic Resins, Inc.

Message:
Nylon 6/6 33% Glass Fiber Reinforced Heat Stabilized Natural

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 33% filler by weight		
Additive	heat stabilizer		
Features	Thermal Stability		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	179	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus - Tangent	8970	MPa	ASTM D790
Flexural Strength	255	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	260	°C	ASTM D648
1.8 MPa, not annealed	252	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	74.0 - 85.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	282 - 304	°C	
Middle Temperature	277 - 299	°C	
Front Temperature	271 - 299	°C	
Nozzle Temperature	266 - 293	°C	
Processing (Melt) Temp	282 - 299	°C	
Mold Temperature	38.0 - 93.0	°C	
Injection Pressure	55.0 - 138	MPa	
Injection Rate	Moderate-Fast		
Holding Pressure	41.0 - 103	MPa	

Back Pressure	0.00 - 1.00	MPa
Cushion	6.35 - 12.7	mm
Injection instructions		

Screw Speed: SlowDecompression: 3.81 to 7.6 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

