

UBESTA 3035 JU5

Polyamide 12
UBE Engineering Plastics, S.A.

Message:

UBESTA 3035 JU5 is a high molecular weight Polyamide 12. It is plasticized and heat stabilized. Most suitable for super flexible hydraulic and pneumatic tubes.

General Information			
Additive	heat stabilizer		
	Plasticizer		
Features	Plasticized		
	Workability, good		
	Good flexibility		
	Thermal Stability		
Uses	Pipe fittings		
Appearance	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	14	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	1.2	%	ISO 294-4
Flow direction	0.80	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.70	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	28		ISO 2039-2
Durometer Hardness (Shore D)	59		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	30.0	MPa	ISO 527-2
Tensile Strain (Break)	300	%	ISO 527-2
Flexural Modulus	200	MPa	ISO 178
Flexural Stress	10.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C, complete fracture	2.0	kJ/m ²	ISO 179/1eA
23°C	No Break		ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, not annealed	70.0	°C	ISO 75-2/B
1.8 MPa, not annealed	40.0	°C	ISO 75-2/A
Melting Temperature (DSC)	162	°C	ISO 3146
CLTE - Flow	2.0E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+10	ohms·cm	IEC 60093

Additional Information

The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357.Tensile Strain at Break, ISO 527: >300%Tensile Stress at Yield, ISO 527: >30 MPaAbrasion Loss, ISO 9352, CS-17, 1000 rev.: 13 mg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

