

Sasol Polymers PE HF150

Linear Low Density Polyethylene

Sasol Polymers

Message:

- Features
- Hexene copolymer
- Good mechanical properties
- Excellent drawdown
- Good heat sealing range
- Good opticals
- Film stiffness
- Applications
- Lamination film
- Liquid packaging film (FFS)

General Information			
Additive	Low smoothness		
	Antioxidation		
	Moderate caking resistance		
Features	Low smoothness		
	Copolymer		
	Optical		
	hexene comonomer		
	Antioxidation		
	Good stripping		
	Good heat sealability		
	Compliance of Food Exposure		
	Moderate caking resistance		
Uses	Packaging		
	Films		
	Laminate		
Agency Ratings	EC 1935/2004		
	FDA 21 CFR 177.1520(a)(3)(i)(c)(1)		
	FDA 21 CFR 177.1520(c) 3.1a		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm ³	ASTM D1505

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	30	µm	
Tensile Strength			ASTM D882
MD: Yield, 30 µm, blown film	12.0	MPa	ASTM D882
TD: Yield, 30 µm, blown film	12.0	MPa	ASTM D882
MD: Broken, 30 µm, blown film	32.0	MPa	ASTM D882
TD: Broken, 30 µm, blown film	26.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Yield, 30 µm, blown film	370	%	ASTM D882
TD: Yield, 30 µm, blown film	510	%	ASTM D882
Dart Drop Impact ¹ (30 µm, Blown Film)	130	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 30 µm, blown film	3.0	g	ASTM D1922
TD: 30 µm, blown film	25	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	67		ASTM D2457
Haze	7.0	%	ASTM D1003
Additional Information			
The above values were calculated from data for 30µm film produced on a 75mm Barmag extruder with 190°C melt temperature using a 2:1 blow ratio.			
Extrusion	Nominal Value	Unit	
Hopper Temperature	180 - 190	°C	
Cylinder Zone 1 Temp.	190 - 200	°C	
Cylinder Zone 2 Temp.	190 - 200	°C	
Cylinder Zone 3 Temp.	190 - 200	°C	
Cylinder Zone 4 Temp.	190 - 200	°C	
Melt Temperature	190	°C	
Die Temperature	190 - 200	°C	
Extrusion instructions			
Screen Pack: 20/40/20 BS meshBlow ratio: >2:1			
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

