

LNP™ LUBRICOMP™ SP003 compound

Polyamide 12
SABIC Innovative Plastics

Message:

LNP LUBRICOMP SP003 is a compound based on Nylon 12 resin containing 15% PTFE/Silicone. Added feature of this material is: Wear Resistant.
Also known as: LNP* LUBRICOMP* Compound SL-4530
Product reorder name: SP003

General Information			
Additive	PTFE + Silicone Lubricant (15%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.90 to 1.1	%	ASTM D955
Across Flow : 24 hr	1.8 to 2.0	%	ASTM D955
Across Flow : 24 hr	1.9	%	ISO 294-4
Flow : 24 hr	1.0	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1380	MPa	ASTM D638
--	1580	MPa	ISO 527-2/1
Tensile Strength			
Yield	37.9	MPa	ASTM D638
Yield	38.0	MPa	ISO 527-2
Break	35.2	MPa	ASTM D638
Break	36.0	MPa	ISO 527-2
Tensile Elongation			
Yield	18	%	ASTM D638, ISO 527-2
Break	24	%	ASTM D638
Break	33	%	ISO 527-2
Flexural Modulus			
--	1380	MPa	ASTM D790
--	1300	MPa	ISO 178
Flexural Stress	44.0	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.23		

vs. Itself - Static	0.14		
Wear Factor - Washer	13.5	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	53	J/m	ASTM D256
23°C ²	4.6	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	680	J/m	ASTM D4812
23°C ³	48	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	5.00	J	ASTM D3763
--	7.80	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	150	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	134	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	146	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	147	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	1.1E-4	cm/cm/°C	
Transverse : -40 to 40°C	1.1E-4	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.12 to 0.20	%	
Rear Temperature	216 to 227	°C	
Middle Temperature	221 to 232	°C	
Front Temperature	227 to 238	°C	
Processing (Melt) Temp	227 to 238	°C	
Mold Temperature	71.1 to 82.2	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

