

LEXAN™ 505RU resin

Polycarbonate

SABIC Innovative Plastics

Message:

LEXAN 505RU is a glass reinforced, flame retardant (FR) grade with non brominated and non chlorinated FR systems and UV stabilization packages. This product is intended for applications to meet WEEE/RoHS regulations as well as various voluntary environmental labels.

General Information			
UL YellowCard	E207780-100059995		
Filler / Reinforcement	Glass fiber reinforced material		
Additive	UV stabilizer		
Features	Chlorine Free		
	Bromine-free		
	Flame retardancy		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	8.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	7.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.60	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Outdoor Suitability	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3600	MPa	ASTM D638
--	3500	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	74.0	MPa	ASTM D638
Yield	72.0	MPa	ISO 527-2/5
Fracture ³	62.0	MPa	ASTM D638
Fracture	60.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	4.0	%	ASTM D638
Yield	3.0	%	ISO 527-2/5
Fracture ⁵	6.0	%	ASTM D638
Fracture	6.0	%	ISO 527-2/5

Flexural Modulus			
50.0mm span ⁶	3200	MPa	ASTM D790
-- ⁷	3500	MPa	ISO 178
Flexural Stress			
--	122	MPa	ISO 178
Yield, 50.0mm span ⁸	114	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	7.0	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	70	J/m	ASTM D256
23°C	90	J/m	ASTM D256
-30°C ¹¹	8.0	kJ/m ²	ISO 180/1A
23°C ¹²	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1200	J/m	ASTM D4812
-30°C ¹³	73	kJ/m ²	ISO 180/1U
23°C ¹⁴	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	25.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	137	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁵	136	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	149	°C	ASTM D1525, ISO 306/B120 11 ¹⁶
--	147	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 40°C	5.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	7.4E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	8.5E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 3		UL 746
Comparative Tracking Index	175	V	IEC 60112
High Amp Arc Ignition (HAI)	PLC 0		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value	Unit	Test Method

Flame Rating			UL 94
0.750 mm, Testing by SABIC	V-2		UL 94
1.50 mm, Testing by SABIC	V-0		UL 94
	5VB		
3.00 mm, Testing by SABIC	5VA		UL 94
Glow Wire Flammability Index (0.750 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	850	°C	IEC 60695-2-13
3.00 mm	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	288 - 310	°C	
Middle Temperature	299 - 321	°C	
Front Temperature	310 - 332	°C	
Nozzle Temperature	304 - 327	°C	
Processing (Melt) Temp	310 - 332	°C	
Mold Temperature	82.2 - 116	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	Type 1, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*3 sp=62mm		
10.	80*10*3 sp=62mm		
11.	80*10*3		
12.	80*10*3		
13.	80*10*3		
14.	80*10*3		
15.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

