

Star L POM D36

Acetal (POM) Copolymer
Eurostar Engineering Plastics

Message:

Star L POM D36 is a Molybdenum Disulfide Lubricated, POM Copolymer Injection Molding Resin

General Information			
Additive	Molybdenum disulfide lubricant		
Features	Copolymer		
	Lubrication		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Molding Shrinkage - Flow (4.00 mm)	2.6 - 3.4	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain (Break)	31	%	ISO 527-2
Flexural Modulus	2200	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ¹ (23°C)	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ² (23°C)	110	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (0.45 MPa, Unannealed, 100 mm Span)	145	°C	ISO 75-2/Be
Melting Temperature (DSC)	169	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	180 - 190	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	180 - 200	°C	
Processing (Melt) Temp	180 - 200	°C	
Mold Temperature	60.0 - 100	°C	
Injection instructions			
Screw Speed: Moderate			
NOTE			

1.	80*10*4
2.	80*10*4
3.	120*10*4

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT