

4MID® 9A20000

Polyamide 66
4Plas

Message:

4MID 9A20000 is a Standard Flow Unfilled PA66

General Information			
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage			
Vertical flow direction	1.4	%	
Flow direction	1.4	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	2.7	%	ISO 62
Moisture Content	< 2000	ppm	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3200	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	85.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C	4.0	kJ/m ²	ISO 179
23°C	5.0	kJ/m ²	ISO 179/B
Charpy Unnotched Impact Strength			ISO 179/eU
-30°C	No Break		ISO 179/eU
23°C	No Break		ISO 179/eU
Notched Izod Impact			ISO 180/1A
-30°C	4.0	kJ/m ²	ISO 180/1A
23°C	5.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	210	°C	ISO 75-2/B
1.8 MPa, not annealed	80.0	°C	ISO 75-2/A
Melting Temperature ²	262	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Flame Rating			UL 94
0.750 mm	V-2		UL 94
1.60 mm	V-2		UL 94
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	270 - 290	°C	
Mold Temperature	50.0 - 90.0	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	50.0 - 100	MPa	
Screw Speed	< 400	rpm	
Injection instructions			
Feed Throat Temperature: 60 - 80 °C Back Pressure: Low			
NOTE			
1.	24 Hrs		
2.	10 K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

