LUMISIL® 885

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-2 Optoelectronics, Lighting Optoelectronics, Electronics LED, Lighting

General Information			
Uses	LEDs		
	Lighting Applications		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.05	g/cm³	ISO 2781
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	75		ISO 868
Tensile Strength	11.0	MPa	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

%

ISO 37

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

80

Tel: +86 21 5895 8519

Phone: +86 13424755533

Tensile Elongation at Break

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

