

# RTP 106CC

Polypropylene Homopolymer

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'  
The data for this material has not been recently verified.  
Please contact RTP Company for current information prior to specifying this grade.

| General Information                |                                                       |                   |             |
|------------------------------------|-------------------------------------------------------|-------------------|-------------|
| Filler / Reinforcement             | Glass fiber reinforced material, 35% filler by weight |                   |             |
| Features                           | Chemical coupling                                     |                   |             |
| RoHS Compliance                    | Contact manufacturer                                  |                   |             |
| Appearance                         | Black                                                 |                   |             |
|                                    | Natural color                                         |                   |             |
| Forms                              | Particle                                              |                   |             |
| Processing Method                  | Injection molding                                     |                   |             |
| Physical                           | Nominal Value                                         | Unit              | Test Method |
| Specific Gravity                   | 1.17                                                  | g/cm <sup>3</sup> | ASTM D792   |
| Molding Shrinkage - Flow (3.18 mm) | 0.30                                                  | %                 | ASTM D955   |
| Water Absorption (23°C, 24 hr)     | 0.040                                                 | %                 | ASTM D570   |
| Hardness                           | Nominal Value                                         | Unit              | Test Method |
| Rockwell Hardness (R-Scale)        | 102                                                   |                   | ASTM D785   |
| Mechanical                         | Nominal Value                                         | Unit              | Test Method |
| Tensile Modulus                    | 8270                                                  | MPa               | ASTM D638   |
| Tensile Strength                   | 103                                                   | MPa               | ASTM D638   |
| Tensile Elongation (Break)         | 2.5                                                   | %                 | ASTM D638   |
| Flexural Modulus                   | 5520                                                  | MPa               | ASTM D790   |
| Flexural Strength                  | 128                                                   | MPa               | ASTM D790   |
| Compressive Strength               | 86.2                                                  | MPa               | ASTM D695   |
| Impact                             | Nominal Value                                         | Unit              | Test Method |
| Notched Izod Impact (3.18 mm)      | 100                                                   | J/m               | ASTM D256   |
| Unnotched Izod Impact (3.18 mm)    | 640                                                   | J/m               | ASTM D4812  |
| Thermal                            | Nominal Value                                         | Unit              | Test Method |
| Deflection Temperature Under Load  |                                                       |                   | ASTM D648   |
| 0.45 MPa, not annealed             | 160                                                   | °C                | ASTM D648   |
| 1.8 MPa, not annealed              | 149                                                   | °C                | ASTM D648   |
| CLTE - Flow                        | 3.4E-5                                                | cm/cm/°C          | ASTM D696   |
| Thermal Conductivity               | 0.35                                                  | W/m/K             | ASTM C177   |
| Electrical                         | Nominal Value                                         | Unit              | Test Method |
| Volume Resistivity                 | 1.0E+15                                               | ohms · cm         | ASTM D257   |

|                                                         |               |       |             |
|---------------------------------------------------------|---------------|-------|-------------|
| Dielectric Strength                                     | 20            | kV/mm | ASTM D149   |
| Dielectric Constant (1 MHz)                             | 2.75          |       | ASTM D150   |
| Dissipation Factor (1 MHz)                              | 1.0E-3        |       | ASTM D150   |
| Arc Resistance                                          | 122           | sec   | ASTM D495   |
| Flammability                                            | Nominal Value | Unit  | Test Method |
| Flame Rating (1.59 mm, Values per RTP Company testing.) | HB            |       | UL 94       |
| Additional Information                                  |               |       |             |
| Mold Shrinkage, ASTM D-955, 0.25in.: 4mil/in.           |               |       |             |
| Injection                                               | Nominal Value | Unit  |             |
| Drying Temperature                                      | 82.2          | °C    |             |
| Drying Time                                             | 2.0           | hr    |             |
| Suggested Max Regrind                                   | 20            | %     |             |
| Rear Temperature                                        | 232 - 274     | °C    |             |
| Middle Temperature                                      | 232 - 274     | °C    |             |
| Front Temperature                                       | 232 - 274     | °C    |             |
| Mold Temperature                                        | 32.2 - 65.6   | °C    |             |
| Injection Pressure                                      | 68.9 - 138    | MPa   |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

