

Ecomass® 1080ZB92

Polyamide 12
Ecomass Technologies

Message:

Ecomass® 1080ZB92 is a Polyamide 12 (Nylon 12) material filled with filler. It is available in North America for injection molding.

Important attributes of Ecomass® 1080ZB92 are:

Good Toughness
Non-Toxic
Rigid

General Information			
Filler / Reinforcement	Filler		
Features	Medium Rigidity		
	Non-Toxic		
	Ultra High Toughness		
Uses	Radiation Shielding		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	6.88	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6450	MPa	ASTM D638
Tensile Strength	34.5	MPa	ASTM D638
Tensile Elongation (Break)	3.8	%	ASTM D638
Flexural Modulus	6410	MPa	ASTM D790
Flexural Strength	49.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	121	°C	
1.8 MPa, Unannealed	107	°C	
Injection	Nominal Value	Unit	
Drying Temperature	73.9	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	232 to 260	°C	
Mold Temperature	65.6 to 82.2	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT