

Michimid K4100GF13-02

Polyamide 6

API Polymers, Inc.

Message:

Michimid K4100GF13-02 is a Polyamide 6 (Nylon 6) product filled with 13% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	93.1	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus - Tangent	5000	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	210	°C	
1.8 MPa, Unannealed	191	°C	
Melting Temperature	215	°C	ASTM D789
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260	°C	
Middle Temperature	271	°C	
Front Temperature	271	°C	
Nozzle Temperature	266	°C	
Processing (Melt) Temp	277	°C	
Mold Temperature	79.4	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT