

Iupilon® GSH2010R2

Polycarbonate

Mitsubishi Engineering-Plastics Corp

Message:

Iupilon® GSH2010R2 is a Polycarbonate (PC) material filled with 10% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Iupilon® GSH2010R2: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage			
Across Flow : 3.20 mm	0.40 to 0.60	%	
Flow : 3.20 mm	0.30 to 0.50	%	
Water Absorption (Saturation, 23°C)	0.14	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4400	MPa	ISO 527-2
Tensile Stress (Break)	82.0	MPa	ISO 527-2
Tensile Strain (Break)	3.8	%	ISO 527-2
Flexural Modulus	3900	MPa	ISO 178
Flexural Stress	130	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	60	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	145	°C	ISO 75-2/B
1.8 MPa, Unannealed	140	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	4.0E-5	cm/cm/°C	
Transverse	6.7E-5	cm/cm/°C	
Electrical	Nominal Value		Test Method
Comparative Tracking Index (CTI)	PLC 3		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.400 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Rear Temperature	270 to 290	°C
Middle Temperature	280 to 300	°C
Front Temperature	290 to 310	°C
Nozzle Temperature	290 to 310	°C
Mold Temperature	80.0 to 120	°C
Injection Pressure	50.0 to 150	MPa
Screw Speed	50 to 100	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

