

Leona™ 14G50

Polyamide 66

Asahi Kasei Chemicals Corporation

Message:

Leona™ 14G50 is a Polyamide 66 (Nylon 66) product filled with 50% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Leona™ 14G50 include automotive, engineering/industrial parts and electrical/electronic applications.

Characteristics include:

Flame Rated

Creep Resistant

Fatigue Resistant

Heat Resistant

Heat Stabilizer

General Information	
UL YellowCard	E48285-240878
Filler / Reinforcement	Glass Fiber,50% Filler by Weight
Additive	Heat Stabilizer
Features	Fatigue Resistant
	Good Creep Resistance
	Heat Stabilized
	High Stiffness
	High Strength
	Medium Heat Resistance
Uses	Automotive Applications
	Electrical/Electronic Applications
	Rods
	Structural Parts

Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.58	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage				Internal Method
Across Flow	0.70	--	%	
Flow	0.40	--	%	
Water Absorption				
Saturation, 23°C	--	1.3	%	
Equilibrium, 23°C, 50% RH	--	1.3	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785, ISO 2039-2
M-Scale	95	80		
R-Scale	118	--		
Mechanical	Dry	Conditioned	Unit	Test Method

Tensile Modulus (23°C)	16900	13000	MPa	ISO 527-2
Tensile Stress				
Break, 23°C	237	183	MPa	ISO 527-2
--	235	170	MPa	ASTM D638
Tensile Elongation				
Break	2.5	4.0	%	ASTM D638
Break, 23°C	2.0	4.0	%	ISO 527-2
Flexural Modulus				
--	14500	9800	MPa	ASTM D790
23°C	13600	11000	MPa	ISO 178
Flexural Strength				
--	390	280	MPa	ASTM D790
23°C	371	269	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles)	--	22.0	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	14	21	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break	95 kJ/m ²		ISO 179
Notched Izod Impact	140	190	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	260	--	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	250	--	°C	ASTM D648
1.8 MPa, Unannealed	255	--	°C	ISO 75-2/A
CLTE - Flow	2.0E-5	--	cm/cm/°C	ASTM D696
Thermal Conductivity	0.40	--	W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	--	ohms	ASTM D257, IEC 60093
Volume Resistivity				
--	1.0E+15	--	ohms·cm	ASTM D257
23°C	1.0E+15	--	ohms·cm	IEC 60093
Dielectric Strength	21	--	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (3.00 mm)	525	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	HB	--		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

