

Staramide PFB42EU

Polyamide 6

Eurostar Engineering Plastics

Message:

Staramide PFB42EU is an UV stabilized Glass Bead and Glass Fiber Reinforced Polyamide 6 Injection Molding Resin

General Information			
Filler / Reinforcement	Glass Bead\Glass Fiber		
Additive	UV Stabilizer		
Features	Good UV Resistance		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Molding Shrinkage - Flow (4.00 mm)	0.44	%	Internal Method
Water Absorption (23°C, 24 hr)	1.9	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5700	MPa	ISO 527-2/1
Tensile Stress (Break)	93.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.6	%	ISO 527-2/5
Flexural Modulus ¹	4700	MPa	ISO 178
Flexural Stress	145	MPa	ISO 178
Flexural Strain at Break ²	4.4	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³ (23°C)	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	20	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵ (1.8 MPa, Unannealed, 64.0 mm Span)	156	°C	ISO 75-2/Af
CLTE			ISO 11359-2
Flow : 23 to 60°C	4.9E-5	cm/cm/°C	
Transverse : 23 to 60°C	9.3E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	230 to 240	°C	
Middle Temperature	240 to 260	°C	
Front Temperature	240 to 270	°C	
Processing (Melt) Temp	240 to 270	°C	

Mold Temperature	60.0 to 80.0	°C
NOTE		
1.	2.0 mm/min	
2.	2.0 mm/min	
3.	80*10*4	
4.	80*10*4	
5.	80*10*4	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

