

Durethan® BKV 20 FN01 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 18 % glass fibers, injection molding, halogen free flame retardant

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 18% filler by weight		
Additive		Flame retardancy		
Features		Halogen-free		
		Flame retardancy		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Resin ID (ISO 1043)		PA GF FR (30+40+72)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.34	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	37.0	--	cm ³ /10min	ISO 1133
Molding Shrinkage				ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	0.60	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.20	--	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	0.30	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.10	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	5.3	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.6	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	7960	4500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	110	60.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	4.9	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	7200	4200	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	--	95.0	MPa	ISO 178/A
23°C ⁶	170	110	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.2	6.0	%	ISO 178/A

ISO Shortname	PA 6, GFHR, 12-080, GF18	--		ISO 1874
Residual Moisture Content	0.030 - 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	50	60	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	< 10	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	40	45	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	218	--	°C	ISO 75-2/B
1.8 MPa, not annealed	200	--	°C	ISO 75-2/A
Vicat Softening Temperature	205	--	°C	ISO 306/B120
Melting Temperature ⁸	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	3.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	8.6E+15	--	ohms	IEC 60093
Volume Resistivity (23°C)	5.3E+17	--	ohms · cm	IEC 60093
Comparative Tracking Index (CTI)	PLC 0	--		UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	V-0	--		UL 94
1.50 mm	V-0	--		UL 94
3.00 mm	5VA	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.800 mm	960	--	°C	IEC 60695-2-12
1.50 mm	960	--	°C	IEC 60695-2-12
3.00 mm	960	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature				IEC 60695-2-13
0.750 mm	750	--	°C	IEC 60695-2-13
1.50 mm	750	--	°C	IEC 60695-2-13
3.00 mm	750	--	°C	IEC 60695-2-13
Oxygen Index ⁹	34	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	

Drying Time - Dry Air Dryer	2.0 - 6.0	hr
Processing (Melt) Temp	250 - 270	°C
Mold Temperature	80.0	°C

NOTE		
1.	60x60x2mm, 80°C MT, 600 bar	
2.	60x60x2mm	
3.	60x60x2mm, 80°C MT, 600 bar	
4.	60x60x2mm	
5.	2.0 mm/min	
6.	2.0 mm/min	
7.	2 mm/min	
8.	10°C/min	
9.	Procedure A	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT