# Novamid® 2030 FC

## Polyamide 66/6 Copolymer

## **DSM Engineering Plastics**

#### Message:

Novamid® 2030 FC is a Polyamide 66/6 Copolymer (Nylon 66/6) material. It is available in Asia Pacific for extrusion or film extrusion. Primary attribute of Novamid® 2030 FC: Flame Rated.

Typical application of Novamid® 2030 FC: Film

General Information	
Uses	Film
Processing Method	Extrusion
	Film Extrusion

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50%			
RH)	2.8	%	ISO 62
Viscosity Number	246	cm³/g	ISO 307
Thermal	Nominal Value	Unit	Test Method
Melting Temperature <sup>1</sup>	200	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flammability Classification (1.50 mm)	НВ		IEC 60695-11-10, -20
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

