

Kepamid® 2330GFH

Polyamide 66

Korea Engineering Plastics Co., Ltd

Message:

KEPAMID 2330GFH is a 30% glass fiber reinforced and heat resistant polyamide-66.

It exhibits good mechanical properties and long term heat resistance.

It is applicable to automotive, electrical, electronic, and industrial parts.

General Information			
UL YellowCard	E120354-220471		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Heat Aging Resistance		
	Medium Heat Resistance		
Uses	Automotive Applications		
	Electrical Parts		
	Electrical/Electronic Applications		
	Industrial Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	0.40 to 0.90	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	186	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus (23°C)	8630	MPa	ASTM D790
Flexural Strength (23°C)	275	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	260	°C	
1.8 MPa, Unannealed	255	°C	
Melting Temperature	260	°C	DSC
Flammability	Nominal Value		Test Method

Flame Rating (0.800 mm)	HB	UL 94
Injection	Nominal Value	Unit
Hopper Temperature	260 to 300	°C
Rear Temperature	260 to 300	°C
Middle Temperature	260 to 300	°C
Front Temperature	260 to 300	°C
Nozzle Temperature	260 to 300	°C
Mold Temperature	40.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT