

Mapex AT0110GN

Polyamide 66

Ginar Technology Co., LTD.

Message:

Mapex AT0110 GN PA6.6 is an impact modified product for low temperature use for injection moulding in natural colour

General Information			
Additive	Impact modifier		
Features	Impact modification		
	Highlight		
	Solvent resistance		
	Good formability		
	Good electrical performance		
	Good chemical resistance		
	Good wear resistance		
	Good weather resistance		
	Fuel resistance		
	Heat resistance, high		
	Oil resistance		
Uses	Low temperature application		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage - Flow (1.60 mm)	2.9 - 3.1	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	80	%	ISO 527-2
Flexural Modulus	1620	MPa	ISO 178
Flexural Stress	76.0	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	70.0	°C	ASTM D648, ISO 75-2/A
Melting Temperature	250	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (3.20 mm)	HB		UL 94
Additional Information			
Notched Izod Impact Strength, ISO 180/1, notch 0.25in: 801 kg cm/cmNotched Izod Impact Strength, ISO 180/1, notch 0.25in, -30°C: 427 kg cm/cm			

Injection	Nominal Value	Unit
Drying Temperature	70.0	°C
Drying Time	4.0	hr
Rear Temperature	250 - 300	°C
Middle Temperature	250 - 300	°C
Front Temperature	250 - 300	°C
Nozzle Temperature	290 - 305	°C
Mold Temperature	30.0 - 100	°C
Injection Pressure	50.0 - 120	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.00 - 0.300	MPa
Screw Speed	60 - 120	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

