

HiFill® PPS GF40 BK

Polyphenylene Sulfide

Techmer Engineered Solutions

Message:

HiFill® PPS GF40 BK is a Polyphenylene Sulfide (PPS) product filled with 40% glass fiber. It can be processed by injection molding and is available in North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.65	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	0.030	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	157	MPa	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Flexural Modulus	14100	MPa	ASTM D790
Flexural Strength	241	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	282	°C	
1.8 MPa, Unannealed	271	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	163	°C	
Drying Time	4.0	hr	
Rear Temperature	288 to 304	°C	
Middle Temperature	316 to 343	°C	
Front Temperature	310 to 332	°C	
Nozzle Temperature	316 to 332	°C	
Processing (Melt) Temp	324 to 338	°C	
Mold Temperature	129 to 163	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

