

# KumhoSunny ABS 730Z

Acrylonitrile Butadiene Styrene  
Shanghai KumhoSunny Plastics Co., Ltd.

Message:  
Kumhosunny ABS730Z is heat resistance ABS with low gloss, high rigidity , toughness and good UV stability.Application:Hair dryer shells,electric oven exterior parts and microwave ovens etc.

| General Information                                  |                                    |                   |              |
|------------------------------------------------------|------------------------------------|-------------------|--------------|
| Features                                             | Good Toughness                     |                   |              |
|                                                      | Good UV Resistance                 |                   |              |
|                                                      | Low Gloss                          |                   |              |
|                                                      | Medium Heat Resistance             |                   |              |
| Uses                                                 | Consumer Applications              |                   |              |
|                                                      | Electrical Parts                   |                   |              |
|                                                      | Electrical/Electronic Applications |                   |              |
| UL File Number                                       | E254819                            |                   |              |
|                                                      | E65424                             |                   |              |
| Forms                                                | Pellets                            |                   |              |
| Processing Method                                    | Injection Molding                  |                   |              |
| Physical                                             | Nominal Value                      | Unit              | Test Method  |
| Density (23°C)                                       | 1.05                               | g/cm <sup>3</sup> | ISO 1183     |
| Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)            | 16                                 | g/10 min          | ISO 1133     |
| Molding Shrinkage (23°C)                             | 0.40 to 0.70                       | %                 | ISO 294-4    |
| Hardness                                             | Nominal Value                      | Unit              | Test Method  |
| Rockwell Hardness (R-Scale, 23°C)                    | 105                                |                   | ISO 2039-2   |
| Mechanical                                           | Nominal Value                      | Unit              | Test Method  |
| Tensile Stress                                       | 45.0                               | MPa               | ISO 527-2/50 |
| Tensile Strain (Break)                               | 30                                 | %                 | ISO 527-2/50 |
| Flexural Modulus <sup>1</sup>                        | 2300                               | MPa               | ISO 178      |
| Flexural Stress <sup>2</sup>                         | 65.0                               | MPa               | ISO 178      |
| Poisson's Ratio <sup>3</sup>                         | 0.38                               |                   | ISO 527      |
| Impact                                               | Nominal Value                      | Unit              | Test Method  |
| Charpy Notched Impact Strength <sup>4</sup>          |                                    |                   | ISO 179      |
| -30°C                                                | 11                                 | kJ/m <sup>2</sup> |              |
| 23°C                                                 | 19                                 | kJ/m <sup>2</sup> |              |
| Charpy Unnotched Impact Strength <sup>5</sup> (23°C) | No Break                           |                   | ISO 179      |

|                                                    |                  |                   |             |
|----------------------------------------------------|------------------|-------------------|-------------|
| Notched Izod Impact Strength <sup>6</sup>          |                  |                   | ISO 180     |
| -30°C                                              | 10               | kJ/m <sup>2</sup> |             |
| 23°C                                               | 18               | kJ/m <sup>2</sup> |             |
| Unnotched Izod Impact Strength <sup>7</sup> (23°C) |                  |                   | ISO 180     |
| No Break                                           |                  |                   |             |
| Thermal                                            | Nominal Value    | Unit              | Test Method |
| Heat Deflection Temperature <sup>8</sup>           |                  |                   |             |
| 0.45 MPa, Unannealed                               | 95.0             | °C                | ISO 75-2/B  |
| 1.8 MPa, Unannealed                                | 82.0             | °C                | ISO 75-2/A  |
| Vicat Softening Temperature                        | 100              | °C                | ISO 306/B50 |
| Electrical                                         | Nominal Value    | Unit              | Test Method |
| Surface Resistivity                                | > 1.0E+15        | ohms              | IEC 60093   |
| Volume Resistivity                                 | > 1.0E+15        | ohms·cm           | IEC 60093   |
| Flammability                                       | Nominal Value    | Unit              | Test Method |
| Flame Rating                                       | HB               |                   | UL 94       |
| Injection                                          | Nominal Value    | Unit              |             |
| Drying Temperature                                 | 80.0 to 85.0     | °C                |             |
| Drying Time                                        | 3.0 to 4.0       | hr                |             |
| Suggested Max Moisture                             | 0.050            | %                 |             |
| Rear Temperature                                   | 190 to 210       | °C                |             |
| Middle Temperature                                 | 210 to 220       | °C                |             |
| Front Temperature                                  | 220 to 235       | °C                |             |
| Nozzle Temperature                                 | 230 to 245       | °C                |             |
| Processing (Melt) Temp                             | 220 to 240       | °C                |             |
| Mold Temperature                                   | 50.0 to 80.0     | °C                |             |
| Back Pressure                                      | 1.00 to 5.00     | MPa               |             |
| Screw Speed                                        | 30 to 70         | rpm               |             |
| NOTE                                               |                  |                   |             |
| 1.                                                 | 2.0 mm/min       |                   |             |
| 2.                                                 | 2.0 mm/min       |                   |             |
| 3.                                                 | 1mm/min          |                   |             |
| 4.                                                 | Condition: 4 J   |                   |             |
| 5.                                                 | Condition: 4 J   |                   |             |
| 6.                                                 | Condition: 5.5 J |                   |             |
| 7.                                                 | Condition: 5.5 J |                   |             |
| 8.                                                 | 120°C/h          |                   |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

