

E-RIALFILL H 07 20 T2

Polypropylene Homopolymer

RIALTI Srl

Message:

Polypropylene homopolymer obtained by recycling of industrial scrap, 20% talc filled
Flowability rate specific for injection molding, good thermal and mechanical characteristics.
Available in versions black color.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Features	Good Flow		
	Good Thermal Stability		
	Homopolymer		
Appearance	Black		
Forms	Regrind		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	1.1	%	
Water Absorption ¹ (23°C, 24 hr)	0.020	%	ISO 62
Ash Content	20	%	ISO 3451
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/20
Yield, 23°C	30.0	MPa	
Break, 23°C	24.0	MPa	
Tensile Strain			ISO 527-2/20
Yield, 23°C	5.0	%	
Break, 23°C	15	%	
Flexural Modulus ² (23°C)	2600	MPa	ISO 178
Flexural Stress (23°C)	46.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	30	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength			ISO 180/1A
-20°C	2.0	kJ/m ²	

23°C	2.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	110	°C	ISO 75-2/B
1.8 MPa, Unannealed	63.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	150	°C	ISO 306/A50
--	92.0	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 335
CLTE - Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	190 to 210	°C	
Mold Temperature	40.0 to 50.0	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	50%RH		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT