

DAUNYL A R300

Polyamide 66

Daunia Trading srl

Message:

DAUNYL A R300 is a polyamide 66 reinforced with 30% glass fibre for injection moulding. It presents high mechanical properties and outstanding dimensional stability. The standard colours are natural and black.

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		Good Dimensional Stability		
Appearance		Black		
		Natural Color		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.35	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage				
Flow	0.25 to 0.35	--	%	ASTM D955
--	0.25 to 0.35	--	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.85 to 0.95	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	110	108		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9500	6000	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	175	120	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	3.0	4.0	%	ASTM D638, ISO 527-2
Flexural Strength	260	215	MPa	ASTM D790, ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	100	150	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	215	--	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	205	--	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	> 240	--	°C	ASTM D1525, ISO 306
Melting Temperature	255 to 265	--	°C	
CLTE - Flow	3.0E-5	--	cm/cm/°C	ASTM D696
Service Temperature				

Continuous	80 to 100	--	°C	
Short Term	150	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+11	ohms	ASTM D257, IEC 60093
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	ASTM D257, IEC 60093
Dielectric Strength	60	40	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index	500	--	V	DIN 53480
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	HB	--		UL 94
Injection	Dry	Unit		
Processing (Melt) Temp	240 to 270		°C	
Mold Temperature	80.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

