

Delrin® 100P NC010

ACETAL RESIN

DuPont Performance Polymers

Message:

High Viscosity Acetal Homopolymer with Improved Processing

General Information			
UL YellowCard	E41938-257616		
Additive	Lubricant		
	Mold Release		
Features	Lubricated		
Uses	Profiles		
	Sheet		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
	Profile Extrusion		
	Sheet Extrusion		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Shear Stress vs. Shear Rate (ISO 11403-1)		
	Specific Volume vs Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)	>POM<		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.6	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.20	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.9	%	
Flow	2.2	%	
Water Absorption			ISO 62

23°C, 24 hr, 2.00 mm	1.4	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	0.30	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	88		
R-Scale	119		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2950	MPa	ISO 527-2
Tensile Stress (Yield)	71.0	MPa	ISO 527-2
Tensile Strain (Yield)	25	%	ISO 527-2
Nominal Tensile Strain at Break	45	%	ISO 527-2
Tensile Creep Modulus			ISO 899-1
1 hr	2700	MPa	
1000 hr	1500	MPa	
Flexural Modulus	2850	MPa	ISO 178
Flexural Stress (3.5% Strain)	77.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	14	kJ/m ²	
23°C	15	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	400	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-40°C	12	kJ/m ²	
23°C	14	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	155	°C	ISO 75-2/B
1.8 MPa, Unannealed	93.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	175	°C	ISO 306/A50
--	160	°C	ISO 306/B50
Melting Temperature ¹	178	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.1E-4	cm/cm/°C	
Flow : -40 to 23°C	1.0E-4	cm/cm/°C	
Transverse	1.1E-4	cm/cm/°C	
Transverse : -40 to 23°C	1.0E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093

Electric Strength	41	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.90		
1 MHz	3.90		
Dissipation Factor			IEC 60250
100 Hz	0.012		
1 MHz	5.5E-3		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.800 mm	HB		
1.50 mm	HB		
Fill Analysis	Nominal Value	Unit	Test Method
Melt Density	1.19	g/cm ³	
Additional Information	Nominal Value	Unit	Test Method
Emission	< 8.00	mg/kg	VDA 275
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

