

Forprene® 6NM901A35

Thermoplastic Vulcanizate

SO.F.TER. SPA

Message:

Forprene® 6NM901A35 is a Thermoplastic Vulcanizate (TPV) material. It is available in Europe, Latin America, or North America for injection molding.

Primary attribute of Forprene® 6NM901A35: REACH Compliant.

Typical applications include:

Automotive

Industrial Applications

Sealing Applications

General Information			
Uses	Automotive Applications		
	Industrial Applications		
	Seals		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.950	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	37		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Set	7	%	ASTM D412
Tensile Stress ¹ (100% Strain)	0.900	MPa	ASTM D412
Tensile Strength ²	3.00	MPa	ASTM D412
Tensile Elongation ³ (Break)	460	%	ASTM D412
Tear Strength ⁴	14.0	kN/m	ASTM D624
Compression Set ⁵ (70°C, 22 hr)	32	%	ASTM D395B
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Rear Temperature	150	°C	
Middle Temperature	160	°C	
Front Temperature	170	°C	
Nozzle Temperature	175	°C	
Mold Temperature	20.0 to 40.0	°C	
NOTE			
1.	Die C		
2.	Die C		
3.	Die C		

4.	Die C
5.	Type 1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

