

Adell Polyamide AS-60

Polyamide 66

Adell Plastics, Inc.

Message:

Adell Polyamide AS-60 is a Polyamide 66 (Nylon 66) material. It is available in North America.

Important attributes of Adell Polyamide AS-60 are:

Good Weather Resistance

Heat Resistant

General Information			
Features	Good Thermal Stability		
	Good Weather Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.3 to 1.6	%	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	86		
R-Scale	121		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	91.0	MPa	ASTM D638
Tensile Elongation (Break)	12	%	ASTM D638
Flexural Modulus	3170	MPa	ASTM D790
Flexural Strength (Yield)	119	MPa	ASTM D790
Compressive Strength	102	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	196	°C	
1.8 MPa, Unannealed	78.9	°C	
Melting Temperature	254 to 266	°C	
CLTE - Flow	7.2E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.25	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

