

LNP™ VERTON™ MV00ASXP compound

Polypropylene

SABIC Innovative Plastics Europe

Message:

LNP VERTON* MV00AS is a compound based on Polypropylene resin containing Long Glass. Added features of this material include: Chemically Coupled.

Also known as: LNP* VERTON* Compound MFX-700-10 HS

Product reorder name: MV00ASXP

General Information			
Filler / Reinforcement	Long Glass Fiber		
Features	Chemically Coupled		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792, ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	10400	MPa	ASTM D638
--	13900	MPa	ISO 527-2/1
Tensile Strength			
Break	131	MPa	ASTM D638
Break	141	MPa	ISO 527-2
Tensile Elongation			
Break	1.9	%	ASTM D638
Break	1.7	%	ISO 527-2
Flexural Modulus			
--	9340	MPa	ASTM D790
--	11100	MPa	ISO 178
Flexural Strength			
--	187	MPa	ASTM D790
--	214	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.34		
vs. Itself - Static	0.52		
Wear Factor - Washer	73.0	10 ⁻⁴ in ³ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	210	J/m	ASTM D256
23°C ²	29	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	66	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			

23°C, Energy at Peak Load	13.0	J	ASTM D3763
--	13.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 64.0 mm Span ⁴	164	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	157	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	160	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	3.4E-5	cm/cm/°C	
Transverse : -40 to 40°C	4.6E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	232 to 243	°C	
Middle Temperature	243 to 254	°C	
Front Temperature	249 to 260	°C	
Processing (Melt) Temp	221 to 249	°C	
Mold Temperature	37.8 to 65.6	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

