

SOLLAMID B 2700 FV 25

Polyamide 6
Krisoll Resinas Plásticas Ltda.

Message:
SOLLAMID B 2700 FV 25 is a Polyamide 6 (Nylon 6) material filled with 25% glass fiber. It is available in Latin America. Primary attribute of SOLLAMID B 2700 FV 25: Flame Rated.

General Information				
Filler / Reinforcement		Glass Fiber,25% Filler by Weight		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.32	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.35 to 0.55	--	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.0	--	%	ASTM D570
Heat Stability	100 to 110	--	°C	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	122	110		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	7000	4500	MPa	ASTM D638
Tensile Strength (23°C)	135	85.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.5	5.5	%	ASTM D638
Flexural Modulus (23°C)	6500	4000	MPa	ASTM D790
Flexural Strength (23°C)	210	120	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	9.0	15	kJ/m ²	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	195	--	°C	
1.8 MPa, Unannealed	180	--	°C	
Melting Temperature	214 to 220	--	°C	
CLTE - Flow	3.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	--	ohms · cm	ASTM D257
Dielectric Strength	22	--	kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
NOTE				
1.	Notch B			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

