

KOPA® KN333G50

Polyamide 66

Kolon Plastics, Inc.

Message:

KOPA®KN333G50 is a polyamide 66 (nylon 66) product, which contains a 50% glass fiber reinforced material. It can be processed by injection molding and is available in North America, Latin America, Europe or Asia Pacific. KOPA®KN333G50 applications include electrical/electronic applications, engineering/industrial accessories and the automotive industry.

Features include:

flame retardant/rated flame

ROHS certification

high strength

good weather resistance

chemical resistance

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Additive	Lubricant		
Features	High tensile strength		
	Good wear resistance		
	Good chemical resistance		
	Good weather resistance		
	Self-lubricating		
Uses	Electrical/Electronic Applications		
	Industrial components		
	Application in Automobile Field		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.58	g/cm ³	ASTM D792
--	1.56	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.20 - 0.40	%	ASTM D955
Water Absorption (Equilibrium)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	125		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	230	MPa	ASTM D638
23°C	250	MPa	ISO 527-2
Tensile Elongation			

Yield	5.0	%	ASTM D638
Fracture, 23°C	2.5	%	ISO 527-2
Flexural Modulus			
--	13200	MPa	ASTM D790
23°C	13000	MPa	ISO 178
Flexural Strength			
--	353	MPa	ASTM D790
23°C	360	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	18	kJ/m ²	ISO 179/1eA
Notched Izod Impact	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	252	°C	ASTM D648
1.8 MPa, not annealed	250	°C	ASTM D648
1.8 MPa, not annealed	255	°C	ISO 75-2/A
Melting Temperature	255	°C	ISO 11357-3
CLTE - Flow	2.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	21	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.60		ASTM D150
Arc Resistance	135	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80 - 100	°C	
Drying Time - Desiccant Dryer	4.0 - 5.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	270	°C	
Middle Temperature	290	°C	
Front Temperature	295	°C	
Nozzle Temperature	300	°C	
Mold Temperature	60 - 80	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

