

Iupilon® ELV2010

Polycarbonate

Mitsubishi Engineering-Plastics Corp

Message:

Wear Resistance Improved

General Information			
UL YellowCard	E41179-100949963		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	9.70	cm ³ /10min	ISO 1133
Molding Shrinkage			
Lateral flow: 3.20mm	0.50 - 0.70	%	
Traffic: 3.20mm	0.50 - 0.70	%	
Water Absorption (Saturation, 23°C)	0.13	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2
Tensile Stress (Yield)	57.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.7	%	ISO 527-2
Nominal Tensile Strain at Break	100	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	142	°C	ISO 75-2/B
1.8 MPa, not annealed	127	°C	ISO 75-2/A
Linear thermal expansion coefficient			ISO 11359-2
Flow	6.4E-5	cm/cm/°C	ISO 11359-2
Lateral	6.8E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value		Test Method
Comparative Tracking Index (CTI)	PLC 4		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.8 mm)	V-2		UL 94

Injection	Nominal Value	Unit
Rear Temperature	270 - 290	°C
Middle Temperature	280 - 300	°C
Front Temperature	280 - 300	°C
Nozzle Temperature	280 - 300	°C
Mold Temperature	70 - 100	°C
Injection Pressure	50.0 - 150	MPa
Screw Speed	50 - 100	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

