

TECACOMP® PA66 TC white 3924

Polyamide 66
Ensinger GmbH

Message:

Main features
high thermal conductivity
very good electrical insulation
Target Industries
electrical engineering
LED lighting technology
mechanical engineering
automotive industry

General Information			
Filler / Reinforcement	Glass fiber reinforced material Ceramic fiber filler		
Features	Heat conduction Insulation		
Uses	LEDs Lighting Applications Application in Automobile Field		
Appearance	White		
Forms	Particles		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm³	
Apparent Density	0.79	g/cm³	ISO 60
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	40	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	26.5	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Transverse flow	0.67	%	ISO 294-4
Flow	0.36	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	1.3	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13000	MPa	ISO 527-2/50
Tensile Stress	105	MPa	ISO 527-2/50
Tensile Strain (Break)	1.5	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method

Charpy Unnotched Impact Strength	25	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	252	°C	ISO 75-2/A
Glass Transition Temperature	50.0	°C	DIN 53765
Melting Temperature	255	°C	DIN 53765
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 45°C	2.5E-5	cm/cm/°C	ISO 11359-2
Flow: 70 to 120°C	2.5E-5	cm/cm/°C	ISO 11359-2
Horizontal: 23 to 45°C	5.0E-5	cm/cm/°C	ISO 11359-2
Horizontal: 70 to 120°C	7.5E-5	cm/cm/°C	ISO 11359-2
Specific Heat	1090	J/kg/°C	DIN EN 821
Thermal Conductivity			DIN EN 821
-- ¹	1.5	W/m/K	DIN EN 821
-- ²	3.5	W/m/K	DIN EN 821
Service Temperature			
long term	120	°C	
short term	180	°C	
Thermal Diffusivity			DIN EN 821
In-plane	1.60	cSt	DIN EN 821
Through-plane	0.700	cSt	DIN EN 821
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+12	ohms	DIN EN 61340
Volume Resistivity	3.6E+13	ohms·cm	DIN EN 61340
Flammability	Nominal Value	Unit	Test Method
Flammability Classification	HB		IEC 60695-11-10, -20
Injection	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	4.0 - 5.0	hr	
Processing (Melt) Temp	260 - 295	°C	
Mold Temperature	100 - 150	°C	
NOTE			
1.	Through-plane		
2.	In-plane		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

