

Durethan® B 31 FCS 000000

Polyamide 6
LANXESS Corporation

Message:
PA 6, non-reinforced, Extrusion, low viscosity, no additives

General Information				
Features		Low Viscosity		
Processing Method		Extrusion		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.14	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (235°C/2.16 kg)	16.0	--	cm ³ /10min	ISO 1133
Water Absorption				ISO 62
Saturation, 23°C	10	--	%	
Equilibrium, 23°C, 50% RH	3.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	140	50.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	2800	800	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	75.0	35.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	4.0	25	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	20	> 50	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2600	700	MPa	ISO 178/A
Flexural Stress ² (3.5% Strain)	90.0	20.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ³ (23°C)	5.0	8.0	%	
ISO Shortname	PA 6,ES, 14-030	--		ISO 1874
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	< 5.0	kJ/m ²	
23°C	5.0	50	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	55 kJ/m ²		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180/1A

-30°C	7.0	7.5	kJ/m ²	
23°C	7.0	50	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	150	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	--	°C	ISO 75-2/A
Vicat Softening Temperature	200	--	°C	ISO 306/B120
Melting Temperature ⁴	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Injection	Dry	Unit		
Drying Temperature - Dry Air Dryer				
	80.0		°C	
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	Pull Rate: 2 mm/min; 50% RH			
4.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT