

LNP™ STAT-KON™ DD000P compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP* STAT-KON* DD000P is a compound based on Polycarbonate resin containing Carbon. Added features of this material include: Electrically Conductive, Exceptional Processing.
Also known as: LNP* STAT-KON* Compound D- EP
Product reorder name: DD000P

General Information			
Filler / Reinforcement	Carbon Fiber		
Features	Electrically Conductive		
	Good Processability		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.60 to 0.80	%	ASTM D955
Across Flow : 24 hr	0.70 to 0.90	%	ASTM D955
Across Flow : 24 hr	0.84	%	ISO 294-4
Flow : 24 hr	0.74	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2760	MPa	ASTM D638
--	2490	MPa	ISO 527-2/1
Tensile Strength			
Yield	57.2	MPa	ASTM D638
Yield	57.0	MPa	ISO 527-2
Break	49.6	MPa	ASTM D638
Break	51.0	MPa	ISO 527-2
Tensile Elongation			
Yield	4.8	%	ASTM D638, ISO 527-2
Break	20	%	ASTM D638
Break	9.9	%	ISO 527-2
Flexural Modulus			
--	2760	MPa	ASTM D790
--	2400	MPa	ISO 178
Flexural Stress	78.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	230	J/m	ASTM D256
23°C ²	21	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	2200	J/m	ASTM D4812
23°C ³	210	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	40.5	J	ASTM D3763
--	40.3	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	135	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	135	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	125	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	126	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	6.7E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	6.6E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	6.5E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	6.4E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+5 to 1.0E+9	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	310 to 321	°C	
Front Temperature	321 to 332	°C	
Processing (Melt) Temp	304 to 327	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT