

PERLEX® R5563

Polycarbonate
A. Schulman Europe

Message:

PERLEX® R5563 is a Polycarbonate (PC) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Important attributes of PERLEX® R5563 are:

Flame Rated
Flame Retardant
Good UV Resistance
UV Stabilized

Typical application of PERLEX® R5563: Electrical/Electronic Applications

General Information			
UL YellowCard	E132739-567482		
Additive	Flame Retardant		
	UV Stabilizer		
Features	Flame Retardant		
	Good UV Resistance		
Uses	Electrical Parts		
Appearance	Opaque		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain (Break)	> 50	%	ISO 527-2
Flexural Modulus	2400	MPa	ISO 178
Flexural Stress	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	45.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	135	°C	ISO 75-2/B
1.8 MPa, Unannealed	130	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating	UL 94		
1.60 mm	V-0		

3.20 mm	V-0	
Glow Wire Ignition Temperature		IEC 60695-2-13
1.00 mm	960	°C
2.00 mm	960	°C
3.00 mm	960	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

