

ELIX™ ABS L3FR

Acrylonitrile Butadiene Styrene

ELIX Polymers, S. L.

Message:

Elix ABS L3FR
flame retardant ABS
ISO Shortname: ABS 1, MGF, 085-25-09-25

General Information			
UL YellowCard	E350602-101011321		
Features	Flame Retardant		
Processing Method	Injection Molding		
Part Marking Code	ABS 1, MGF, 085-25-09-25		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	50.0	cm³/10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	105	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2400	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	42.0	MPa	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	4.0	kJ/m²	
23°C	8.0	kJ/m²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	40	kJ/m²	
23°C	60	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	89.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	85.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	85.0	°C	ISO 306/B50
--	88.0	°C	ISO 306/B120
CLTE - Flow (23 to 55°C)	9.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+17	ohms · cm	IEC 60093
Relative Permittivity			IEC 60250

23°C, 100 Hz	3.00		
23°C, 1 MHz	3.00		
Dissipation Factor			IEC 60250
23°C, 100 Hz	7.0E-3		
23°C, 1 MHz	8.0E-3		
Comparative Tracking Index (Solution A)	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT