

Flexalloy® 9602-72FR

Polyvinyl Chloride Elastomer

Teknor Apex Company

Message:

Flexalloy® 9602-72FR is a Polyvinyl Chloride Elastomer (PVC Elastomer) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of Flexalloy® 9602-72FR are:

RoHS Compliant

Flame Retardant

Good Flexibility

Heat Resistant

Sunlight Resistant

Typical application of Flexalloy® 9602-72FR: Wire & Cable

General Information			
Features	Flame Retardant		
	High Heat Resistance		
	Low Temperature Flexibility		
	Sunlight Resistant (720 hours)		
Uses	Cable Jacketing		
Wire Types	SCE		
	SE		
	SEOW		
	SEW		
	SJEOW		
	SJEW		
	STEOW		
	STEW		
Agency Ratings	VW-1		
	UL Class 11		
	UL Class 12		
	UL Class 36		
	UL Class 43		
UL QMTT2 .E73402			
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method

Durometer Hardness (Shore A, 15 sec)	72		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	13.3	MPa	ASTM D638
Tensile Elongation (Break)	390	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	105	°C	ASTM D794
Brittleness Temperature	-48.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	6.16		
1 MHz	4.10		
Dissipation Factor			ASTM D150
1 kHz	0.11		
1 MHz	0.11		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	29	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

